

PRODUCT DATA SHEET

Revision Date: 02/02/2012

Print Date: 06/20/2018

MICROCEMENT READY FINE

1. DESCRIPTION: POLYMER REINFORCEMENT READY TO USE 1 COMPONENT

DESCRIPTION: MICROCEMENTO READY TO USE

It is a cementitious coating ready to decorative use of stucco effect, its formulation contains arid selected extremely hard, special resins with high adhesion and highly waterproof, high elasticity free of cracking even when there are structural stresses, its high impermeability they confer properties for the application in zones with humidity, not darkening by effect of the water, very good resistance to wear and scratches and excellent adhesion to many supports, being of only 1 component, it does not need mixing, application with trowel and very easy application, 1 only product packaging, very easy to work, highly decorative and very easy to apply. Not suitable for swimming pools or surfaces in constant immersion. **two .**

2. TECHNICAL CHEMICAL PHYSICAL CHARACTERISTICS .

FINISH - MATE

COLOR - No color (color at the time of use with color toner)

SOLIDS IN WEIGHT - 100%

DRYING TIME - 2 to 3 hours

EXPIRATION - 1 year from date of production in original closed containers.

STORAGE - The temperature must not be less than + - 5° and more than + - 25° during the storage.

APPROXIMATE PERFORMANCE - 400 to 500 grms x kgs and hand

3. MAIN PROPERTIES

- √ Breathable
- √ Waterproof
- √ **It does** not yellow
- √ High elasticity
- √ Very good adhesion
- √ High deformability mineral coating
- √ High mechanical resistance
- √ Low thermal diffusion
- √ Fireproof
- √ Aseptic
- √ Decorative
- √ 1 component

4. SURFACE TREATMENT AND RECOMMENDATIONS

Do not apply on powdery surfaces or contaminated with products that inhibit adhesion as waxes, oils, etc., it is advisable to apply a first coat of microcement medium or base ready to use if is to regularize.

It is not advised for floors and floors of medium traffic

Regularize the surface to be treated by sanding previously, if the surface is very absorbent as plaster pladur, etc advisable to apply previously tapaporos to water (hidroprimer)

It is recommended to seal the last hand of fine micromortero with polyurethane to water to achieve greater impermeability and more resistance to roze.

Do not apply at temperatures below 8 degrees or above 30, 35 degrees.

Do not leave the container exposed to the sun and with the lid open, you can produce skins in the container.

5. FIELDS OF APPLICATION

Especially suitable for decoration by micro-cement system, walls, furniture , shower trays, etc.

7. FORMATS

Packaging of 5 kgs